

Typical Properties

TESTED PROPERTY	RESULT
Width GSF Method	59 inches
Weight ASTM D 3774	11.0 oz/yd ²
Chatillon Hand ASTM D 4032	6.00 lbf
Height Hydrostat AATCC Method 127	90+ cm
Spray Rating AATCC Method 22	100
Bag Test, 8 & 24 hrs GSF Method	Pass
Water Permeability After Cold Crack ASTM D 751	60+ cm With no visual signs of cracking
Heat Buildup Test (Temperature Reduction °F) ASTM D 4803	25°F